

## Willys Harvest Tan - custom mix

March 4, 2006

Sean Collins

### PPG Deltron 2000 DBU (Deltron Basecoat Urethane) series paint

Color	PPG #	pint	quart	gallon
Red Oxide	DMD 622	5.3	10.7	42.7
Transparent Red Oxide	DMD 623	102	204.1	816.2
Universal Mixing Base - Maroon	DMD 629	3.2	6.4	25.6
Medium Chrome Yellow	DMD 639	17.6	35.2	140.8
Transparent Yellow Oxide	DMD 641	2.9	5.8	23.0
Yellow Oxide	DMD 642	73.3	146.6	586.2
Strong Black	DMD 647	69.9	139.7	558.9
Weak Black	DMD 648	42.7	85.3	341.3
Basecoat White	DMD 663	162.3	324.6	1298.3
Basecoat Balancer (binder)	DMD 695	207.6	415.1	1660.1

Units are "PPG weights", not grams, ounces or anything standard that I know of. Any PPG shop will know what they are.

Reduce at 1:1.5 ratio with PPG DRR1185 reducer for spraying. (1 part paint, 1.5 parts reducer). Don't reduce any more paint than you plan to use at one time. Once reduced, the paint is only good for a couple of days.

This is a basecoat/clearcoat system. Clearcoat w/ PPG Omni MC260 clear with MH167 hardener (slow drying), or MH168 hardener (fast drying). Slow drying produces a softer finish that is easier to color sand. Your painter will know best.

Normal clearcoat is glossy, so if you want that "original" semi/low gloss look, use PPG DX 685 gloss reducer.

Unfortunately, this formula is ONLY good for PPG Deltron DBU series paint. It will not work for other makes or types of paint. Sorry about that, but it's what my painter uses.